

Journal of Vocational Health Studies

https://e-journal.unair.ac.id/JVHS

THE EFFECT OF 50% EDAMAME BEAN (GLYCINE MAX L. MERRIL) EXTRACTS ON THE SURFACE ROUGHNESS OF HEAT-CURED ACRYLIC RESIN

PENGARUH EKSTRAK EDAMAME (GLYCINE MAX L. MERRIL) 50% TERHADAP KEKASARAN PERMUKAAN RESIN AKRILIK HEAT-CURED

Lusi Hidayati ¹⁶, Yohana Maria Penga ^{1*0}, Leliana Sandra Devi ², Ayudia Yohanna Widya Kusumastuti ³⁰

¹ Department of Oral Biology, Material and Dental Technology, Faculty of Dentistry, University of Jember, Jember, Indonesia

² Department of Orthodontics, Faculty of Dentistry, University of Jember, Jember, Indonesia

³ Department of Prosthodontics, Faculty of Dentistry, University of Jember, Jember, Indonesia

ABSTRACT

Background: Edamame bean (Glycine max L. Merril) extract is an alternative to denture cleanser because it contains antifungal and antibacterial compounds, such as flavonoids. However, flavonoids may increase the surface roughness of heat-cured acrylic resin. **Purpose:** This research aims to analyze the effect of 50% edamame bean extract as a denture cleanser on the surface roughness of heat-cured acrylic resin. **Method:** Twenty four square shaped heat-cured acrylic resin plates of 10 x 10 x 2 mm were divided into four groups: A1, A2, B1, and B2. Each group was immersed in distilled water (A1 for four days and A2 for 11 days) and 50% edamame bean extract (B1 for four days and B2 for 11 days). The surface roughness was measured using a surface roughness tester TR 220. The data were then analyzed using the Two Way ANOVA test followed by the Tukey HSD test with a significance value of p-value < 0.05. **Result:** The average surface roughness in heat-cured acrylic resin increased in 50% edamame extract immersion for four and 11 days. The highest increase was experienced in 50 % edamame extract significantly affects the surface roughness for four days and 11 days. **Conclusion:** Edamame extract significantly affects the surface roughness of heat-cured acrylic resin after immersion for four and 11 days.

ABSTRAK

Latar belakang: Ekstrak kacang edamame (Glycine max L. Merril) merupakan salah satu alternatif pembersih gigi tiruan karena mengandung senyawa antijamur dan antibakteri, seperti flavonoid. Namun, senyawa flavonoid diketahui dapat meningkatkan kekasaran permukaan resin akrilik tipe heat-cured. Tujuan: Penelitian ini bertujuan untuk menganalisis pengaruh ekstrak kacang edamame 50% sebagai pembersih gigi tiruan terhadap kekasaran permukaan resin akrilik heat-cured. Metode: 24 buah pelat persegi resin akrilik heat-cured berukuran 10 x 10 x 2 mm dibagi menjadi empat kelompok: A1, A2, B1, dan B2. Masing-masing kelompok direndam dalam aquades (A1 selama 4 hari dan A2 selama 11 hari) dan ekstrak kacang edamame 50% (B1 selama 4 hari dan B2 selama 11 hari). Kekasaran permukaan diukur menggunakan surface roughness tester TR 220. Data kemudian dianalisis menggunakan uji Two Way ANOVA yang dilanjutkan dengan uji Tukey HSD dengan nilai signifikansi p-value < 0.05. Hasil: Rata-rata kekasaran permukaan resin akrilik heat-cured meningkat setelah perendaman dalam ekstrak edamame 50% selama empat dan 11 hari. Peningkatan tertinggi terjadi setelah perendaman selama 11 hari dengan nilai 0.158 µm. Sebaliknya, kelompok perendaman dalam aquadest mencatat kekasaran permukaan paling rendah, baik setelah empat hari maupun 11 hari. Kesimpulan: Ekstrak edamame berpengaruh secara signifikan terhadap kekasaran permukaan resin akrilik heat-cured setelah perendaman selama empat dan 11 hari.

Journal of Vocational Health Studies p-ISSN: 2580–7161; e-ISSN: 2580–717x

Original Research Article *Penelitian*

ARTICLE INFO

Received 06 November 2023 Revised 17 November 2023 Accepted 13 March 2024 Available Online 21 March 2025

Correspondence: Yohana Maria Penga

E-mail : yohana@unej.ac.id

Keywords:

Edamame, Denture cleanser, Surface roughness, Heat-cured acrylic resin

Kata kunci:

Edamame, Pembersih gigi tiruan, Kekasaran permukaan, Resin akrilik *heat-cured*

DOI: 10.20473/jvhs.V8.I3.2025.200-205 Copyright © Journal of Vocational Health Studies. Open access under Creative Commons Attribution-Non Commercial-Share A like 4.0 International Licence (CC-BY-NC-SA)

INTRODUCTION

Heat-cured acrylic resin is the most commonly used denture base material. Heat-cured acrylic resin, known as acrylic resin, has experienced thermal activation polymerization (Anjai *et al.*, 2018). This material has a gingiva like texture and color, making it aesthetically pleasing, affordable, and easy to manipulate and repair. However, heat-cured acrylic resin is also porous and tends to absorb fluid (Naini, 2015).

Denture bases in contact with saliva form Acquired Dental Pellicle (ADP) and generate plaque formation, which increases the accumulation of microorganisms in the oral cavity, especially Candida albicans. This condition results in denture stomatitis (Dama, 2013; Wirayuni, 2017). Periodic cleaning using a denture cleanser is essential to prevent this possibility. However, chemical denture cleansers are reported to increase the surface roughness of heat-cured acrylic resin due to its acid content. Studies suggest using natural or herbal ingredients to minimize this drawback (Dewi *et al.*, 2020).

Edamame (Glycine max L. Merril) is a soybean from the legume group, harvested at the peak of ripening before reaching the hardening period. This plant is originally from Japan. Edamame contains essential compounds such as flavonoids, saponins, isoflavones, alkaloids, and tannins, which have antifungal and antibacterial properties (Abd-Alla et al., 2019; Abdel-Hadya et al., 2019). A previous study proved that edamame extracts at a concentration of 50 mg/ml could inhibit the growth of Candida albicans (Igboabuchi and Ilodibia, 2018; Kristiana et al., 2022). In addition, other studies also show that 50% of edamame extracts effectively inhibit the number of Streptococcus mutans colonies (Devi et al., 2023). However, flavonoid compounds in edamame in contact with heat-cured acrylic resin might cause an increase in the surface roughness of heat-cured acrylic resin.

Surface roughness is crucial for dentures since it affects their quality and longevity and induces bacteria adhesion. The ideal cleanser should keep the mechanical and physical characteristics of the denture base resin the same after extended usage (Porwal *et al.*, 2017; Sharma *et al.*, 2017). For reference, the surface roughness of a heat-cured acrylic resin denture base is acceptable if the value is not more than 0.2 μ m (Onwubu and Mdluli, 2022; Vinagre *et al.*, 2023).

The surface roughness of heat-cured acrylic resin dentures generally increases as dimensional changes because of the duration of use (Arafa, 2016). Those changes might happen during intraoral use. Ningsih *et al.* (2020) suggested that after 1 to 3 years of wear. If adjusted to the contact time between the edamame extract and the acrylic resin plate for 15 minutes (in short-term soaking), the usage period of one year

is equivalent to four days, and three years is equal to a soaking time of 11 days (Arruda *et al.*, 2015). Thus, we chose those periods to analyze the possibility of 50% of edamame extracts changing surface roughness on prolonged use and whether it is still clinically tolerable.

MATERIAL AND METHOD

Specimen preparation

Twenty four heat-cured acrylic resin specimens were fabricated according to the manufacturer's guidelines using conventional flasking and pressurepack techniques. The acrylic resin was placed in a squareshaped cuvette with a size of 10 x 10 x 2 mm (based on the *American Dental Association* (ADA) specification No. 12). The polymerization process of the resin was carried out by placing the flask in boiling water at 100 °C for 20 minutes. The cuvette was left until it reached room temperature before opening. Subsequently, the acrylic sample was smoothed with 500 number scouring paper until the surface was flat and smooth. Then, the acrylic resin specimens were immersed in distilled water for 48 hours and in artificial saliva for one hour.

Preparation of edamame bean extract

The variant of edamame that we used in this research is MF 116 (PT Mitratani Dua Tujuh, Jember, Indonesia). First, edamame beans were dried in an oven at 50 °C for one day. The dried edamame seeds were then ground into powder and sieved. Subsequently, maceration was carried out using 70% ethanol solvent at a 1 : 5 (gr/ml) ratio for three days. The obtained filtrate was then evaporated using a rotary evaporator (Siddiq, 2016). Finally, 50% edamame bean extract was obtained by diluting 1.5 ml extract in 1.5 ml distilled water.

Immersion process

Twenty-four specimens of acrylic resin (n = 6/ group) were distributed into two control groups and two treatment groups, namely A1 and A2 (immersion in distilled water for four days and 11 days, respectively), and B1 and B2 (immersion in 50% edamame bean extract for four and 11 days, respectively). Duration of four and 11 days for immersion was equivalent to using a denture cleanser solution for one year and three years, respectively.

The measurement of surface roughness (Ra)

The surface roughness of the samples before and after treatment was measured using a surface roughness tester TR 220. Measurements are taken on one side of the sample on three different lines. Each sample's average surface roughness (Ra) was then noted and analyzed.

Statistical analysis

The average surface roughness (Ra) data were analyzed using a Statistical Package for The Social Sciences 25.0 (SPSS for Macbook; SPSS, Chicago, IL, USA). The data obtained were analyzed through *Two Way ANOVA*, followed by a *Tukey HSD* test at a % confidence level of 95% ($\alpha = 0.05$).

RESULT

Parametric statistical analysis using the *Two-Way* ANOVA is shown in the Table 1. Table 1 represents a significance value of 0.027 (*p*-value < 0.05), which means that there is a significant difference in the average surface roughness (Ra) between the control and treatment groups. Furthermore, the *Tukey HSD* test illustrates a substantial difference between each group with a value of 0.000 (*p*-*value* < 0.05) in the 50% edamame extract group for four days and 11 days. While in the distilled water (control) group for four days and 11 days it showed no significant difference with a value of 0.232 (*p*-*value* > 0.05).

Figure 1 presents each group's average surface roughness (Ra) before and after immersion. The highest Ra value was experienced in 50% edamame bean extract immersion for 11 days with a value of 0.158 μ m (increase by 0.026 μ m). In contrast, the lowest was observed in both control groups (increase by 0.015 and 0.014 μ m, respectively). The group immersed in 50% edamame bean extract for four days underwent an increase in Ra value by 0.020 to 0.141 μ m.

Table 1.	Tukey	HSD test	on all group	s' average	surface roug	hness (Ra)

	Distilled water (control) for 4 days	Distilled water (control) for 11 days	50% edamame extract for 4 days	50% edamame extract for 11 days
Distilled water (control) for 4 days	-	.232	.000	.000
Distilled water (control) for 11 days	.232	-	.000	.000
50% edamame extract for 4 days	.000	.000	-	.000
50% edamame extract for 11 days	.000	.000	.000	-



Figure 1. Average surface roughness (Ra) of heat-cured acrylic resin before and after treatment

DISCUSSION

The average surface roughness (Ra) of the group soaked in 50% edamame bean extract for four and 11 days experienced the highest increase in surface roughness value compared to the control group. This significant difference may be caused by the contact between the acrylic resin plate and the active compounds in the edamame extract, namely flavonoids (phenolic compounds), which cause chemical damage to the surface of the heat-cured type acrylic resin plate, increasing surface roughness (Dwimartha et al., 2018). This finding supports previous study (Wirayuni and Saputra, 2021) that a longer immersion time might increase the surface roughness of the heat-polymerized acrylic resin denture base. However, in this research, we tried to determine whether the 50% edamame bean extract increases the Ra in an acceptable range.

Our finding showed that although 50% edamame bean extract increases the Ra value of both treatment groups, they did not exceed the tolerance threshold of denture base surface roughness, which is less than 0.2 μ m. If the surface roughness is greater than 0.2 μ m, it leads to a corresponding increase in plaque accumulation, raising the risk of periodontal inflammation and caries (Kodir *et al.*, 2017; Vinagre *et al.*, 2023).

The roughness generated by edamame extract likely appeared because of its flavonoids (phenols) compound. Phenol is a stronger acid than alcohol and water (Saputera et al., 2021). The H⁺ ion in that compound will fill the gap by diffusion between the polymer chain bonds of the ester group (COOH), damaging the C = Odouble bond in the heat-cured type acrylic resin and leading to unstable polymer chain bonds. The ester group is more readily hydrolyzed and forms many cracks on the surface of the heat-cured acrylic resin. The number of cracks causes the surface to be uneven and increases the surface roughness of the heat-cured acrylic resin (Wirahadikusumah et al., 2020). However, in this research, we used the optimum concentration of 50% to give an effective cleansing result with minimum damage. The result shows that even though it caused surface roughness, the value is still acceptable for one to three years of use.

The distilled water is pure water with H₂O molecules (no other ionic elements). This solution served as a control because it contains no active substances that accelerate the separation of polymer chains of heat-cured acrylic resins (Ozyilmaz and Akin, 2019; Savitri *et al.*, 2022). However, this research discovered that the Ra value of acrylic resin samples of both control groups insignificantly increased after immersion in aquadest (*p*-value > 0.05). The alterations of roughness value in the control groups might have occurred due to water absorption, which can lead to fatigue and change in dimensions, leading to cracks in the resin (Ozyilmaz and Akin, 2019).

Polymethyl methacrylate in acrylic resin is a hydrophilic compound because of its polar ester group (COOH) (Rifdayanti et al., 2019). Consequently, this acrylic resin can absorb or bind liquids strongly (Sofya et al., 2017). This absorption happens through diffusion, by which a substance moves through a gap or space on the surface of a heat-cured acrylic resin. Water molecules that penetrate the polymethyl methacrylate chain will occupy a position between the polymer chains, causing the polymer chains to push apart. A separated polymer chain will form spaces on the surface of the acrylic resin, called porosity, so that the surface of the heat-cured acrylic sheet becomes rougher (Kalasworojati et al., 2020). According to a study by Fouda et al. (2019), the surface of acrylic resin with more pores also had the roughest texture.

Another effect of heat-cured acrylic resin's liquid absorption and microporosity properties is allowing the base to absorb salivary proteins easily and form an *Acquired Dental Pellicle* (ADP). This pellicle becomes a reservoir of *Candida albicans* growth, resulting in denture stomatitis, so cleaning the denture chemically using a chemical cleanser is necessary. Based on our research, 50% edamame bean extract can be an ideal alternative denture cleanser for heat-cured acrylic resin for one to three years.

Edamame is known to contain essential compounds such as flavonoids (phenols), saponins, isoflavones, and tannins that act as antibacterial and antifungal agents (Igboabuchi and Ilodibia, 2018; Abdel-Hadya et al., 2019; Peiretti et al., 2019; Kristiana et al., 2022). Phenol is a stronger acid compared to alcohol and water because of its chemical formula (C₄H₂OH), where the structure has a hydroxyl group (OH) (Saputera et al., 2021). The acidic compounds containing H⁺ ions can reduce the surface tension of heat-cured type acrylic resins so that the H⁺ ions can easily penetrate between the acrylic resin molecules. The ion will then fill the gap by diffusion between the polymer chain bonds of the ester group (COOH) so that the H^+ ion will damage the C = O double bond in the heat-cured type acrylic resin. This event leads to unstable polymer chain bonds. The ester group is more readily hydrolyzed and forms many cracks on the surface of the heat-cured acrylic resin. The number of cracks causes the surface to be uneven and increases the surface roughness of the heat-cured acrylic resin (Wirahadikusumah et al., 2020).

CONCLUSION

The 50% edamame bean extract significantly affects the surface roughness of heat-cured acrylic resin after immersion for four and 11 days. The highest Ra value was recorded in the immersion for 11 days but is still clinically acceptable.

ACKNOWLEDGMENTS

This work was only possible with the facilities and support from the Faculty of Dentistry at the University of Jember. We confirm that there are no known conflicts of interest associated with this publication, and there has been no significant financial support for this work that could have influenced its outcome.

REFERENCE

- Abd-Alla, H.I., Taie, H. a. A., Abd-Elmotaleb, M.M., 2019. Comparative Phytochemical and Investigation of Five Glycine max (L.) Merril Genotypes. Asian Journal of Pharmaceutical and Clinical Research Vol. 12(2), Pp. 523–534.
- Abdel-Hadya, H., El-Wakila, E.A., Nasrb, S.M., 2019. Characterization and Evaluation of Antimicrobial and Cytotoxic Activities of Glycine Max Methanol Extract. International Journal of Pharmaceutical Research (09752366) Vol. 11(2), Pp. 418.
- Anjai, M., Damiyanti, M., Triaminingsih, S., 2018. Effect of Immersion Time in Denture Cleanser on The Transverse Strength of Heat-Cured Acrylic Resin. Journal of Physics: Conference Series Vol. 1073(6), Pp. 062012.
- Arafa, K.A.O., 2016. Effect of Different Denture Base Materials and Changed Mouth Temperature on Dimensional Stability of Complete Dentures. International Journal of Dentistry, Pp. 7085063.
- Arruda, C.N.F., Sorgini, D.B., Oliveira, V. de C., Macedo, A.P., Lovato, C.H.S., Paranhos, H. de F.O., 2015.
 Effects of Denture Cleansers on Heat-Polymerized Acrylic Resin: A Five-Year-Simulated Period of Use.
 Brazilian Dental Journal Vol. 26(4), Pp. 404-408.
- Dama, C., 2013. Pengaruh Perendaman Plat Resin Akrilik Dalam Ekstrak Kayu Manis (Cinnamomum burmanii) terhadap Jumlah Blastospora Candida albicans. E-Gigi Vol. 1(2), Pp. 1-5.
- Devi, L.S., Setyorini, D., Hasna, H.S., Ramadhani, V., 2023. Effectiveness of Edamame Extract (Glycine max L. Merril) Against Streptococcus mutans on Orthodontic Appliances Base. Health Notions Vol. 7(2), Pp. 33-37.
- Dewi, Z.Y., Insaeni, R.S., Rijaldi, M.F., 2020. Perbedaan Perubahan Nilai Kekasaran Permukaan Plat Resin Akrilik Polimerisasi Panas dengan Plat Nilon Termoplastik setelah Direndam Alkalin Peroksida. Padjadjaran Journal of Dental Researchers and Students. Vol. 4(2), Pp. 153-158.
- Dwimartha, A.J., Saputera, D., Wijayanti, T.F., 2018. Efek Ekstrak Jahe Putih Kecil 70% terhadap Nilai Kekerasan Basis Resin Akrilik. Dentin Vol. 2(1), Pp. 40-44.

- Fouda, S.M., Gad, M.M., Ellakany, P., Al-Thobity, A.M., Al-Harbi, F.A., Virtanen, J.I., Raustia, A., 2019. The Effect of Nanodiamonds on Candida Albicans Adhesion and Surface Characteristics of PMMA Denture Base Material - An in Vitro Study. Journal of Applied Oral Science: Revista FOB Vol. 27, Pp. e20180779.
- Igboabuchi, N.A., Ilodibia, C., 2018. A Study on The Antioxidant and Antimicrobial Activities of Seed and Leaf Extracts of Glycine max (L) Merr. Asian Journal of Research in Botany Vol. 1(1), Pp. 1-8.
- Kalasworojati, R.T., Soesetijo, A., Parnaadji, R.R., 2020. Pengaruh Rebusan Minyak Atsiri Daun Sirih Merah (Piper Crocatum) sebagai Bahan Pembersih Gigi Tiruan Resin Akrilik terhadap Kekasaran Permukaan dan Perubahan Warna. STOMATOGNATIC - Jurnal Kedokteran Gigi Vol. 17(2), Pp. 50-53.
- Kodir, K., Tanti, I., Odang, R.W., 2017. Surface Roughness of Denture Bases After Immersion in The Fishcake Vinegar Solution. Journal of Physics: Conference Series Vol. 884(1), Pp. 012075.
- Kristiana, D., Hidayati, L., Nabil, H.R., 2022. The Effectiveness of Edamame (Glycine Max (L.) Merril) Extract as Acrylic Resin Denture Cleaning on the Number of Candida albicans. Odonto : Dental Journal Vol. 9(1), Pp. 88-94.
- Naini, A., 2015. Pengaruh Berbagai Minuman terhadap Stabilitas Warna Resin Akrilik. Stomagtonatic. STOMATOGNATIC - Jurnal Kedokteran Gigi Vol. 8(2), Pp. 74-77.
- Ningsih, D.S., Rahmayani, L., Mubarak, Z., 2020. The Duration of using Denture Against Plaque
- Onwubu, S.C., Mdluli, P.S., 2022. Comparative Analysis of Abrasive Materials and Polishing System on The Surface Roughness of Heat-Polymerized Acrylic Resins. European Journal of Dentistry Vol. 16(3), Pp. 573-579.
- Ozyilmaz, O.Y., Akin, C., 2019. Effect of Cleansers on Denture Base Resins' Structural Properties. Journal of Applied Biomaterials & Functional Materials Vol. 17(1), Pp. 2280800019827797.
- Peiretti, P.G., Karamać, M., Janiak, M., Longato, E., Meineri, G., Amarowicz, R., Gai, F., 2019. Phenolic Composition and Antioxidant Activities of Soybean (Glycine max (L.) Merr.) Plant during Growth Cycle. Agronomy Vol. 9(3), Pp. 153.
- Porwal, A., Khandelwal, M., Punia, V., Sharma, V., 2017. Effect of Denture Cleansers on Color Stability, Surface Roughness, and Hardness of Different Denture Base Resins. The Journal of the Indian Prosthodontic Society Vol. 17(1), Pp. 61-67.
- Rifdayanti, G.U., Firdaus, I.W.A.K., Sukmana, B.I., 2019. Pengaruh Perendaman Ekstrak Batang Pisang Mauli 25% dan Daun Kemangi 12,5% terhadap Nilai Kekasaran Permukaan (Nilai Kekasaran Permukaan) Basis Akrilik menggunakan Resin Akrilik Tipe Heat Cured). Dentin Vol. 3(3), Pp. 75-81

- Saputera, W.H., Putrie, A.S., Esmailpour, A.A., Sasongko, D., Suendo, V., Mukti, R.R., 2021. Technology Advances in Phenol Removals: Current Progress and Future Perspectives. Catalysts Vol. 11(8), Pp. 998.
- Savitri, R.P.A., Naini, A., Parnaadji, R., Kristiana, D., 2022. Pengaruh Lama Perendaman Resin Akrilik Heat Cured pada Ekstrak Daun Tembakau (Nicotiana tabacum) 50% terhadap Perubahan Warna (Effect of Resin Soaking Time on Heat Cured on 50% Tobacco Leaf Extract (Nicotiana tabacum) on Color Change. Padjadjaran Journal of Dental Researchers and Students Vol. 6(3), Pp. 290-297.
- Sharma, P., Garg, S., Kalra, N.M., 2017. Effect of Denture Cleansers on Surface Roughness and Flexural Strength of Heat Cure Denture Base Resin-An In vitro Study. Journal of Clinical and Diagnostic Research: JCDR Vol. 11(8), Pp. ZC94-ZC97.
- Siddiq, R.H.B.H.F., 2016. Uji Aktivitas Antioksidan Ekstrak Etanol Biji Edamame (Gylcine max L. Merril) dengan Metode DPPH. Jurnal Ilmiah Farmasi Akademi Farmasi Jember Vol. 1(1), Pp. 27-32.

- Sofya, P.A., Rahmayani, L., Purnama, R.R.C., 2017. Effect of Soft Drink Towards Heat-Cured Acrylic Resin Denture Base Surface Roughness. Padjadjaran Journal of Dentistry Vol. 29(1), Pp. 59-64.
- Vinagre, A., Barros, C., Gonçalves, J., Messias, A., Oliveira, F., Ramos, J., 2023. Surface Roughness Evaluation of Resin Composites after Finishing and Polishing Using 3D-Profilometry. International Journal of Dentistry, Pp. e4078788.
- Wirahadikusumah, A., Pratiwi, D., Andany, H.C., 2020. Pengaruh Minuman Kemasan terhadap Kekasaran Basis Gigi Tiruan Sebagian Lepasan (Kajian Berdasarkan Perbedaan Derajat Keasaman). Jurnal Kedokteran Gigi Terpadu Vol. 2(1), Pp. 27-30.
- Wirayuni, K.A., 2017. Akumulasi Streptococcus mutans pada Basis Gigi Tiruan Lepasan Plat Nilon Termoplastik dan Resin Akrilik. Interdental Jurnal Kedokteran Gigi (IJKG) Vol. 13(2), Pp. 28-31.
- Wirayuni, K.A., Saputra, I.M.H.D., 2021. Immersion of Heat Polymerized Acrylic Resin Dental Base in Arak Bali Against Surface Roughness. Interdental Jurnal Kedokteran Gigi (IJKG) Vol. 17(1), Pp. 22-26.